

The product is a liquid concrete admixture that interacts with various active chemicals present in its content. These chemicals react with by-products of hydration in fresh concrete, forming a crystalline structure in the pores and capillary voids of the concrete. This process enhances the waterproofing properties of the concrete.

■ Fields of Application

- Foundations, basement, and underground floors
- Water reservoirs and treatment plants
- Swimming pools and sewage systems
- Dams and irrigation channels
- Tunnels, canals, and ports
- Elevator shafts
- Underground parking structures
- Concrete pipes and precast concrete elements

■ Advantages

- Fills capillary voids and micro-cracks up to 0.4 mm within the concrete structure.
- Provides permanent and structural waterproofing effects in concrete.
- Reduces the passage of water and other liquids.
- Suitable for concrete pouring in all weather conditions.
- Resistant to both positive and negative water pressure.
- Non-toxic.
- Easy application, ensuring no disruption to work schedules.

1 Preparation

M17 MX Liquid should be added to the concrete mixer just before the concrete is poured. Approximately 1% of the total cement content in the concrete mix should be added. Then, mix for at least 10 minutes at high speed using a concrete mixer to ensure thorough distribution and activation.

2 Consumption

M17 MX Liquid should be used at a maximum of 1% of the cement weight in the concrete. The typical usage rate is 3-5 kg per cubic meter of concrete.

3 Health and Safety

During use and storage, ensure the product is not in the same environment as food items. Avoid contact with skin, eyes, and mouth; if contact occurs, wash thoroughly with plenty of water and soap. Keep out of reach of children. For detailed information, refer to the MSDS form.

4 Dikkat Edilecek Hususlar

- Shake the container well before use.
- To avoid issues with homogeneity in low slump concrete, ensure the slump in the mixer is not low (minimum 14-15 cm).
- To maintain the designed water/cement ratio for the concrete, reduce the concrete mix water by 0.8 kg for every 1 kg of M17 MX Liquid added.
- For homogeneous mixing of M17 MX Liquid in the concrete, it must be added to the transmix and mechanically mixed.
- Aggregates used in the concrete to which M17 MX Liquid will be applied must be clean and within the correct sieve ranges.

5 Packaging

10 kg plastic can 30 kg plastic can

6 Storage Life

Must be protected from freezing and can be stored in a dry environment at temperatures above +5°C for up to 12 months in unopened packaging.



TECHNICAL DATAS

Material Composition	Inorganic Mix
Appearance	Slightly cloudy liquid
Density	1,1 kg/l (+20°C)
Application Temperature	Suitable for all weather conditions for concrete pouring
Shelf Life	12 months in unopened packaging, stored in a dry environment
Packaging	10 kg canister, 30 kg canister

Legal Notes

Merks Construction Chemicals Inc. provides the information and application recommendations here in good faith, based on the current knowledge and experience of Merks Construction Chemicals under normal conditions and in accordance with its recommendations. Due to the practical diversity of application surfaces and areas, users of Merks Construction Chemicals products must ensure they apply the correct product under appropriate conditions and in the right location, strictly following the information and instructions provided by Merks Construction Chemicals for specific purposes. Merks Construction Chemicals is not responsible for any damages that may occur otherwise. Users must test the suitability of the product for the intended application and purpose. Merks Construction Chemicals reserves the right to change the properties of its products. Users should always obtain the latest version of the technical data sheet from Merks Construction Chemicals and verify if it is the most recent edition for the respective product.

Notes

This product data sheet includes all technical information based on laboratory experiments. Actual values may vary due to application and site conditions.